



KIPP-2 K-PUR INDOOR

Marking Paint for sports floors

Type of product:	Polyurethane based 2-K PUR lining colour, solvent-reduced and highly abrasion-proof for sports halls. Test report 31/98030 of FMPA Stuttgart.					
Fields of application:	Excellent adhesive strength on linoleum (Linodur), PVC, PUR, composition rubber, prefinished and unfinished parquet floors. Particular rubber floors require a proper pre-treatment with special primers (consultation required).					
Preparation of surface:	The floor must be completely dry and free of dust, grease and oil. Cleaning agents and wax must be completely removed. Measure the layout lines, mark them on both sides with adhesive tape and clean with line cleaner (see data sheet). Mix 2 K PUR Marking Colour Indoor comp. A + B and spread quickly and evenly with a smooth brush. Remove adhesive tape as quickly as possible.					
Mixing Proportions:	Comp. A + B parts by weight 88 : 12					
Preparation time:	Approx. 2 hrs. at 20°C					
Drying time:	Dry after 2 hrs; full load-bearing capacity after 48 hrs					
Consumption:	200 – 250g/m ²					
Layer thickness:	Approx. 100 µm					
Package sizes:	Comp. A: 1 can of 440g; comp. B: 1 tube of 60g					
Standard colours for the sports area:	yellow	app.	RAL 1021	light-blue	app.	RAL 5012
	orange	app.	RAL 2004	green	app.	RAL 6018
	red	app.	RAL 3000	white	app.	RAL 9016
	dark-blue	app.	RAL 5010	black	app.	RAL 9017
	violet	app.	RAL 4008	dark-green	app.	RAL 6029
	grey	app.	RAL 7040			
Storage ability:	With unopened packages and dry storage: Comp. A at least 18 months Comp. B at least 12 months					
Precautionary measures:	During application ensure a constant supply of fresh air at all times. Furthermore all precautionary information, warnings and safety measures can be found on the individual packages. All safety and accident prevention procedures as outlined in respective professional association guidelines are to be observed.					

All instructions are the result of our broad experiences and of scientific trials. Because of the varied processing and working conditions these instructions are non-committal.